Technical Services

Vital Statistics

Durx 670

(55% cellulose/45% polyester, nonwoven)

Technical Services provides information on Berkshire products, quality programs and services.

Berkshire's demanding QA
program has been developed to
evaluate the suitability of Berkshire
products to perform various
functions. In addition to
guaranteeing consistent product
quality, the data generated by these
tests is vital to Berkshire's quality
assurance and product
development.

Berkshire's quality system is certified to the ISO 9002 standard. If you would like more information Regarding Berkshire's QA Program or Test Methods please contact a sales representative or the Customer Service Department.

Berkshire Corporation River Street Great Barrington, MA 01230 800-242-7000

www.berkshire.com

Basis Weight (g/m ²)	68.2
Caliper (µm)	280
Density (g/cc)	0.244
Fibers (/cm²)	98
Particles (≥ 0.5μm):	
(biaxial shake) (x 10 ³ /cm ²)	25
(dry flex) (particles/cu ft)	2400
Absorbency (cc/m ²)	304
Specific Absorbency (cc/g)	4.4
Time To 1/2 Sorbtion (sec)	2
Extractables:	
H ₂ O (%)	0.067
2-Propanol (%)	0.025
lons (ppm):	
Na ⁺	14
K ⁺	5.4
Ca ⁺⁺	260
Mg ⁺⁺	25

(Average of data as of 07/02)

Constitution of the consti

