

Technical Services

Vital Statistics

Technical Services provides information on Berkshire products, quality programs and services.

Berkshire's demanding QA program has been developed to evaluate the suitability of Berkshire products to perform various functions. In addition to guaranteeing consistent product quality, the data generated by these tests is vital to Berkshire's quality assurance and product development.

Berkshire's quality system is certified to the ISO 9002 standard. If you would like more information Regarding Berkshire's QA Program or Test Methods please contact a sales representative or the Customer Service Department.

Berkshire Corporation
River Street
Great Barrington, MA 01230
800-242-7000

www.berkshire.com

Durx 770

(55% cellulose/45% polyester, non-ionic binder, nonwoven)

Basis Weight (g/m ²)	66.3
Caliper (μm)	253
Density (g/cc)	0.262
Fibers (/cm ²)	5.5
Particles (≥ 0.5μm):	
(biaxial shake) (x 10 ³ /cm ²)	9.5
(dry flex) (particles/cu ft)	130
Absorbency (cc/m ²)	258
Specific Absorbency (cc/g)	3.9
Time To 1/2 Sorbtion (sec)	2
Extractables:	
H ₂ O (%)	0.34
2-Propanol (%)	0.42
Ions (ppm):	
Na ⁺	63
K ⁺	6.0
Ca ⁺⁺	280
Mg ⁺⁺	40

(Average of data as of 07/02)

Berkshire

